






-NOTES-

1. MAT'L: ROPE, POLYETHYLENE-DACRON, 3-STRAND.
2. MATERIAL MAY BE CUT BY HOT WIRE METHOD OR TAPE, CUT AND HEAT SEAL ENDS, THIS IS TO PREVENT UNRAVELING OF STRANDS AND TO BOND FILAMENTS.
3. TO MAKE A LOOP, USE AN EYE SPLICE, (SEE ILLUSTRATION BELOW FOR INSTRUCTIONS TO BEGIN LOOP), MAKE 4 FULL TUCKS OF EACH STRAND. TRIM TO APPROX. 3" FROM LAST TUCK AND HEAT SEAL ENDS. COVER BACK END OF SPLICE WITH 6 TURNS OF VINYL PLASTIC TAPE.



LATEST EC NO:		REV.	DATE	CHANGED BY	RESP ENGINEER
97040705		-	-----	---	WEST
				DO NOT SCALE THIS DWG	THIRD ANGLE PROJECTION  ISO DUAL DIMENSIONS IN=INCH, MM=MILLIMETER
DRN BY:	DATE	TITLE:			SIZE
QUALLS	04-08-97	EYE SPLICE			B
					DWG NO: SAM1896-2

CONFIDENTIAL: THIS DRAWING AND ITS CONTENTS ARE CONFIDENTIAL AND THE EXCLUSIVE PROPERTY OF HUBBELL A.B. CHANCE COMPANY. NO PUBLICATION, DISTRIBUTION OR REPRODUCTION MAY BE MADE WITHOUT THE WRITTEN CONSENT OF HUBBELL A.B. CHANCE COMPANY. © 2000 HUBBELL/A.B. CHANCE. UNPUBLISHED - ALL RIGHTS RESERVED UNDER THE COPYRIGHT LAWS